

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 11-302045

(43)Date of publication of application : 02.11.1999

(51)Int.Cl.

C04B 7/02

(21)Application number : 10-113280

(71)Applicant : TAIHEIYO CEMENT CORP

(22)Date of filing : 23.04.1998

(72)Inventor : NAKAJIMA YUTAKA
SUGAYA HIDEYUKI
GOTO KOJI

(54) CEMENT

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain a cement improved flowability and viscosity while maintaining its separation resistance and having good work efficiency.

SOLUTION: The cement contains gypsum consisting essentially of gypsum dihydrate and gypsum hemihydrate. The total amt. of the gypsum dihydrate and gypsum hemihydrate in the gypsum is ≥ 60 wt.% ≥ 50 wt.% of the total amt. is gypsum hemihydrate and α -gypsum hemihydrate accounts for ≥ 50 wt.% of the gypsum hemihydrate.

LEGAL STATUS

[Date of request for examination]

31.01.2005

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]